An in-vitro Study Comparing Shear-Peel Band Strength of

Untreated and Sandblasted Orthodontic Bands Using

Md. Kalim Ullah, Mitali Bora

(Page 41-43)

Conventional Glass Lonomer Cements

ORIGINAL PAPER

An in-vitro Study Comparing Shear-Peel Band Strength of Untreated and Sandblasted Orthodontic Bands using Conventional Glass Lonomer Cements

Ullah Md. Kalim¹, Bora Mitali²

Received on September 30, 2015; editorial approval on December 14, 2015

ABSTRACT

Objectives: To compare the shear-peel band strength of untreated (non-sandblasted) and sandblasted orthodontic bands using two conventional glass ionomer cements- KetacTM-Cem Radiopaque (3M, ESPE) and GC Gold Label Type-1 (GC, Corporation). Methodology: 50 freshly extracted human mandibular third molars were selected and randomly assigned groups of 25 sample each for specific cements with and without sandblasting. Shear-peel band strength in megapascals were obtained by debanding the cemented bands for each group's specimen using an Instron Universal Testing Machine. Data was analyzed with ANOVA followed by a Tukey test. Results: An increase of 72.4% in the retentive strength was observed with sandblasted orthodontic bands cemented with Ketac[™] Cem and about 76.2% of retentive strength with sandblasted one cemented with GC type-1 glass ionomer cement in comparison to untreated bands. Conclusion: Statistically significant differences were noted between non-sandblasted and sandblasted bands groups. The retentive force was increased to almost three quarter folds with sandblasted bands, irrespective of cement used.

Key words: Orthodontic bands, Glass Ionomer Cements, Shear peel strength, Sand-blast

INTRODUCTION

Glass ionomer cements have become the most commonly used cement for retention of orthodontic bands because of their favorable properties of fluoride release and uptake, microbial inhibition and adhesion to both enamel and metal, low solubility in the oral fluids.

Despite improved retention of bands with glass ionomer cements a few literature (Norris et al;¹ Mirzahi;² Stirrups;³ Durning,⁴ etc.), reveals that failure still occurs in clinical orthodontic practice. The commonest site of bond failure occurs at the band- cement interface.⁵ With such a kind of failure, contemporary research has focused into clinical performance of surface treatment of orthodontic bands to improve retention,⁶ of which sandblasting has become the preferred one.

AIMS AND OBJECTIVES

The aims and objectives of this in vitro study was to compare the shear-peel band strength between untreated (nonsandblasted) and sandblasted stainless steel orthodontic bands using two types of conventional glass ionomer luting cements-KetacTM- Cem Radiopaque, 3M, ESPE and GC Gold Label Type-1 (GC, Corporation).

METHODSAND MATERIALS

A total of 50 freshly extracted human mandibular third molars with intact enamel surface and free of any signs of demineralization were selected and stored in 10% formalin solution before being used for the study which was conducted in Regional Dental College, Guwahati in 2009. Optimally sized stainless steel molar bands material (Size-180 \times 005, 8 Feet, Libral Traders, India) were cut and closely adapted for each tooth. The teeth were randomly assigned and reassigned to four groups consisting of 25 samples in each group.

Group 1: Each tooth was banded using non-sandblasted orthodontic band material with KetacTM- Cem.

Group 2: Each tooth was banded using sandblasted orthodontic band material with KetacTM- Cem.

Address for correspondence:
¹ Registrar, Department of Dentistry
(Corresponding Author)
Assam Medical College and Hospital, Dibrugarh, Assam, India
Email: drk_ullah@yahoo.com
Mobile: +91 9678564607
² Professor, Department of Orthodontics
Regional Dental College, Guwahati, Assam, India

Group 3- Each tooth were banded using non-sandblasted orthodontic band material with GC Type 1.

Group 4- Each tooth was banded using sandblasted orthodontic band material with GC Type 1.

Each tooth was completely embedded into a block (25x15x30mm) of self-cure acrylic resin upto the cemento-enamel junction such that the long axis of the tooth lies parallel to the long axis of the acrylic block. In order to facilitate the retention of tooth into the block, a retentive wire of 0.9 mm diameter was passed through a hole of (diameter 1-1.5 mm) drilled near the furcation area of each tooth An acrylic block of same size was specially designed consisting of two loops of 0.9 mm diameter stainless steel wire of equal lengths. This loops engages through the molar tubes of the band and allowed all forces to be directed parallel to the long axis of the tooth during debanding.

Sandblasting (**Figure 2**) of the band material was performed using a sandblaster (Renfert, Variobasic, Germany) which was held at a distance of 2cm from the blaster nozzle and then spraying with a stream of 99.6% micro aluminium oxide particles (Korox 110, Bego, Germany) against the inner (luting) surface of the metal band under 60-80psi of air pressure, until a uniform frosty appearance on the surface was achieved.

First part of the investigation involved measuring the force in an Instron machine (**Figure 1**) required to deband stainless steel non-sandblasted (NS) bands using KetacTM-Cem and GC Type-1 cements, consisting of 25 samples in each group respectively.

The de-banded teeth were cleaned with a scaler and pumice to remove any remaining cement, followed by rinsing with distilled water and then dried. The tooth was then immediately fitted with the new sandblasted bands.

Second part of the investigation involved measuring the force required to deband stainless steel sandblasted (S) bands using KetacTM-Cem and GC Type-1 cements. Each tooth, which served as the samples for the first part of the study were used again.

Calculation of Shear-Peel Band Strength (SPBS)

After twenty-four hours of cementation, the shear debanding force was applied for each specimen using an Instron Universal Testing Machine (Model 4444) in a tensile mode at a cross head speed of 1mm/min. The shear-peel band strength (SPBS) of cemented band was calculated in Megapascals (MPa) for each of the groups cemented with non-sandblasted and sandblasted bands using the following formula.

Shear band strength = $\frac{\text{Breaking load (debanding force in Newton)}}{2}$



Figure 1 Debanding done in Instron



Figure 2 Sandblasting Procedure

RESULTS AND OBSERVATION

Descriptive statistics including the mean, standard deviation, minimum and maximum values for the shear-peel band strength between sandblasted and non-sandblasted bands for each group were calculated (Table I). The level of significance was established at P < 0.05. Statistical analyses were performed using Windows MS excel Software SPSS (v9.0) Program. A one-way analysis of variance (ANOVA) followed by multiple comparisons Tukey HSD posthoc test was used to determine whether statistically significant differences existed among the various groups.

Table 1 Summary statistics for the mean shear peel band strength of different groups

Groups	n	Breaking load (Force)		Surface	Retentive strength (MPa)		
		Kilogram	Newton	area of Band (mm ²)	Mean	SD	Range
1	25	7.147	70.112	174.680	0.402 ^a	0.080	0.238 -0.554
2	25	12.398	121.625	176.111	0.690 ^b	0.221	0.345 -1.228
3	25	18.410	180.603	175.892	1.023 ^c	0.284	0.530 -1.896
4	25	32.565	319.460	176.542	1.803 ^d	0.531	1.038 -2.842
Overall	100	17.845	175.059	175.806	0.991	0.608	0.238 -2.842
Values having different superscripts (a,b,c,d) differ significantly							
(p<0.05) between groups. n- Number of samples; SD-Standard							
Deviation.							

The order of mean SPBS with their standard deviation from greatest to least is as follows:

GC Type-1 (S) > GC Type-1 (NS) > KetacTM Cem- (S) > KetacTM Cem (NS).

or Gr.4 > Gr.3 > Gr.2 > Gr.1

The Tukey test (Table II) shows significant differences on comparison of cements between Non-Sandblasted and Sandblasted bands (n=25).

An increase of 72.4% in the retentive strength observed from non-sandblasted to sandblasted orthodontic bands cemented with KetacTM Cem and about 76.2% of retentive strength with sandblasted GC type-1 glass ionomer cement was observed. This showed superior retention after sandblasting. (**Table III**).

CDOUDS	GROUPS						
GROUPS	1	2	3	4			
1		0.290*	0.623*	1.403*			
2	0.290*		0.333*	1.113*			
3	0.623*	0.333*		0.780*			
4	1.403*	1.113*	0.780*				
* p <0.05 indi	cates significa	nt values; non	comparable	entries are			
designated as -							

Table 2 Tukey posthoc test for statistical significance between groups

Table 3 The percentage (%) of increase in retentive strength from non-sandblasted to sandblasted samples

Cements	NS-bands	S-bands	% Increase
Ketac TM Cem	0.400	0.690	72.414
GC-Type I	1.023	1.803	76.246
NS-Non-Sandb	lasted; S- Sa	indblasted	

DISCUSSION

The present study concurs with the findings of most investigators who demonstrated an increase in band strength after sandblasting stainless steel band material.

The findings of this study are in agreement with those of Seeholzer H, Dasch W^7 who compared groups of orthodontic patients banded with either copper cement or conventional glass ionomer cement. The study showed a considerable increase (30%) in adhesion when the inner surfaces of the bands were sandblasted.

The present study also supports the findings of Millet, McCabe and Gordon⁸. The authors recorded an increase of 27% in bond strength after sandblasting the bands cemented with glass ionomer cement.

Wood and Paleczny⁵ conducted an invitro investigation on twenty extracted human mandibular third molars to evaluate the force required to cause debanding of untreated and sandblasted bands using three different types of cements-zinc phosphate, polycarboxylate and glass lonomer cements. The same bands were then sandblasted and reused. They observed that there was a phenomenal increase of almost 100% in band retention strength after sandblasting the inner surface of the bands.

Miller and Zernik⁶ also did a invitro study on bovine maxillary incisors and found that the mean shear strengths was improved on sandblasting with stainless steel discs cemented with glass ionomer cement.

Aggarwal et al⁹ compared the shear-peel band strength of 5 orthodontic cements using both factory and in-office microetched bands. In this study, the significantly superior band retention of factory-etched bands over the sandblasted bands was found.

Hodges et al¹⁰ Millet et al¹¹ were also with the opinion that there was improved band retention with sandblasted/ micro-etched bands.

Although this study established greater shear peel band strength with sandblasted band material, in order to come to a decisive conclusion, further research has to be done with greater number of samples. Bands are subjected to stresses like torsion, tensile or shear or a combination of all of these, and it is difficult to precisely measure and quantify these forces. Even there are no validated devices to measure the actual debanding forces in vivo. Moreover the cleaning procedure to remove cement remnant are always accompanied by degree of enamel loss.

CONCLUSION

Current research has shown that sandblasting is a preferred method of surface treatment of metals to improve band strength. The sandblasting process enhances the retentive nature of the stainless steel orthodontic bands by increasing its inner surface area and thinning the oxide layer of the stainless steel band.

The following conclusions can be drawn:

1. The mean retentive force increased to almost three quarter folds on sandblasting the inner surface of the orthodontic bands materials.

2. GC Type-1 demonstrated highly significant (P<0.001) retentive strength ability compared to Keta^{cTM} Cem Radiopaque Glass ionomer cement.

Conflict of interest: None declared.

Ethical clearance: Taken.

Source of funding: None declared.

Declarations: (1) The Article is original with the author(s) and does not infringe any copyright or violate any other right of any third parties; (2) The Article has not been published (whole or in part) elsewhere, and is not being considered for publication elsewhere in any form, except as provided herein; (3) All author (s) have contributed sufficiently in the Article to take public responsibility for it and (4) All author (s) have reviewed the final version of the above manuscript and approve it for publication.

REFERENCES

- Norris DS, McInnes Ledoux, Weinberg. Retention of orthodontic bands with new fluoride releasing cements. AJO 1986;89:206-211.
- 2. Mirzahi E. Glass Ionomer Cements in orthodontics an update. Am J Orthod Dentofacial Orthop 1988;93:505-507.
- 3. Stirrups DR A Comparative clinical trial of a Glass lonomer and a Zinc phosphate cement for securing orthodontic bands. British Journal of Orthodontics 1991;18:15-20.
- Durning P, McCabe JF and Gordon PH. A laboratory investigation into cements used to retain orthodontic bands. British Journal of Orthodontics 1994;21:27-32.
- 5. Wood DP, Paleczny GJ, Johnson L. The effect of sandblasting on the retention of orthodontic bands. Angle Orthod 1996;66(3):207-214.
- 6. Miller S, Zernik J. Sandblasting of bands to increase bond strength. JCO 1996;4:217-222.
- 7. Seeholzer H, Dasch W. Banding with a Glass lonomer Cement JCO 1988;XXII(3):165-169.
- Millet DT, McMable JF Bennett TG, Gordon PH. The effect of sandblasting on the retention of first molar orthodontic bands cemented with Glass lonomer Cement. BJO 1995;22:161-9.
- Aggarwal Manish, Foley Timothy F and Douglas. A Comparison of Shear-Peel Band Strengths of 5 Orthodontic Cements. Angle Orthod 2000;70:308–316.
- Hodges SJ, Gilthrope MS and Hunt NP. The effect of microetching on the retention of orthodontic molars bands: a clinical trial. European Journal of Orthodontics 2001;23:91–97.
- 11. Millett DT, Cummings A, Letters S, Roger E and Love J. Resimmodified glass ionomer, modified composite or conventional glass ionomer for band cementation? An in vitro evaluation. European Journal of Orthodontics 2003;25:609–614.